



URSA XPS D N-III L

Thickness d_N [mm] 30	Thermal conductivity λ_D [W/(m ² K)] 0,033	Thermal resistance R_D [m ² K/W] 0,90	Reaction to fire E
-----------------------------------	---	--	------------------------------

	URSA XPS D N-III		
	DoP-No: 49XPSDN320061	http://dop.ursa-insulation.com	
	EN 13164:2012+A1:2015 Factory made extruded polystyrene (XPS) foam products Thermal Insulation for Buildings T1-CS(10Y)200-DS(70,90)-DLT(2)5-WL(T)0,7		


URSA Deutschland GmbH, Carl-Friedrich-Benz-Str. 46-48, 04509 Delitzsch www.ursa.de

/EU/ -T1-CS(10Y)200-DS(70,90)-DLT(2)5-WL(T)0,7
/DE/ Anwendung nach DIN 4108-10: DAA-dm,DEO-dm,WZ
Bemessungswert der Wärmeleitfähigkeit gemäss DIN 4108-4: 0,034 [W/(m²K)]
/CH/ $\lambda_D = 0,033$ [W/(m²K)] gemäß SIA 279
RF 3(cr)
/AT/ Produktart: XPS-G20 nach ÖNORM B6000



011-7D076

2127022



8 435062 212290

Q-8B01-L6 14200630

Length [mm] 1250	Width [mm] 600
Piece(s) 14	Surface [m ²] 10,500
Edge 	